

JC630 4.2 Polyurethane Clearcoat

Background

JC630 is a two component 4.2 VOC polyurethane clearcoat that is designed to maximize speed and appearance and may be used in either cross flow, air dry or downdraft force cure spray booths.

JC630 4.2 Polyurethane Clearcoat

Clear

JC630 4.2 Polyurethane Clearcoat

Hardener

JH6360 4.2 Polyurethane Hardener-Fast

JH6370 4.2 Polyurethane Hardener-Medium

JH6380 4.2 Polyurethane Hardener-Slow

JH6390 4.2 Polyurethane Hardener-Extra Slow

Compatible Substrates

Automotive Refinish Basecoats

Preparation

Allow basecoat color a minimum of 30 minutes and a maximum of 24 hours before clearing. After 24 hours the basecoat should be lightly sanded before applying JC630.

Mixing

Ratios



JC630 : JH63XX
4 : 1



Pot life is 1.5 - 2 hours at 70°F (21°C)

Additives

JX993 10% to RTS quart

JX994 0.5 oz. to RTS quart

Clean Up

Clean spray guns, gun cups, storage pots thoroughly with JR Reducers, General Purpose solvent or other clean up solvent after each use. Follow EPA guidelines for proper storage and disposal of solvent-borne waste paint.

Application

Coats



2 - 3 coats

Air pressure



HVLP 8 - 10 psi at the air cap
Conventional 50 - 60 psi at the gun

Gun setup

1.3 - 1.5 mm or equivalent

Dry Times

Between coats



5 - 10 minutes at 70°F (21°C)

With JH6360 Hardener

Dust: 5 - 10 minutes

Tack: 30 - 50 minutes

Tape / Polish: 2 - 4 hours

Force dry: 15 minutes at 140°F (60°C)

Recoat: 8 hours or overnight at 70°F (21°C)

With JH6370, JH6380, JH6390

Dust: 10 - 15 minutes

Tack: 50 - 60 minutes

Tape / Polish: 2 - 4 hours / 6 - 8 hours

Force dry: 20 minutes at 140°F (60°C)

Recoat: 8 hours or overnight at 70°F (21°C)

IR (Infrared)

12 - 15 minutes

Properties

VOC

Package 3.54 lbs /gal (424 gm/l)

Applied Less exempts 4:1 4.18 lbs /gal (501gm/l)

Film build per coat

Applied (4:1) 1.2 mils

Square foot coverage at 1 mil

Applied (4:1) 560 sq. ft. / gal., no transfer loss

Precautionary Information:

The contents of this package may have to be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels of all components, since the mixture will have the hazards of all its parts. Spray equipment must be handled with due care and in accordance with manufacturer's recommendations. Follow label directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

Medical Response:

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434-4515; IN CANADA (514) 645-1320.

Material Safety Data Sheet:

Material Data Safety Sheets for the PPG products mentioned in this publication are available through your PPG Shop-Line Distributor. To the best of our knowledge, the technical information in this bulletin is accurate; however, since PPG Industries is constantly improving its coating and paint formulas, the current technical data may vary somewhat from what was available when this bulletin was printed. Contact your Shop-Line Distributor for the most up-to-date information.